



Yellow Petroleum Jelly  
Grade PPJI

CHARACTERISTIC	ACCEPTED LIMIT	METHOD
Kinematic viscosity at 100 °C	4.5-6 cSt	ASTM D - 445
Congeling Point	54-58 °C	ASTM D - 938
Penetration Consistency	110-150(0.1mm)	ASTM D - 937
Color ( Lovibond)	Max1.7Y	IP-17 Method A 33mm cell
Acidity or Alkalinity	According to test method	B.P2007

Applications: Industrial manufacturing, Lubrication

Packaging: 180 Kg New steel sealed drums

T: +61 3 909 88601

F: +61 3 909 88602

E:[info@persiana.com.au](mailto:info@persiana.com.au)

Office Address: Level 40, 140 William Street, Melbourne, VIC 3000, Australia